

VELOSIT® WP 101

High Strength Cementitious Waterproofing Slurry

DATA SHEET



HYCHEM

velosit

VELOSIT WP 101 is a cementitious waterproofing slurry for concrete and masonry.

VELOSIT WP 101 is a shrinkage compensated cementitious waterproofing slurry with very quick strength development. VELOSIT WP 101 gains strength a lot faster than the current standard products reducing or completely eliminating the need for days of water curing and protection. VELOSIT WP 101 creates a rigid abrasion resistant coating layer on the substrate.

VELOSIT WP 101 is the result of many years in the field testing and research. VELOSIT WP 101 is a shrinkage compensated cementitious waterproofing slurry with very quick strength development.

TYPICAL APPLICATIONS

Waterproofing

- of basements and below grade
- of potable water structures
- of elevator pits
- against rising dampness in walls
- underneath tiles and natural stones
- Negative side underneath flexible waterproofing membranes
- of prefabricated garage roofs
- Approved - Standards AS4020:2005 Potable Water
- Prime coat to fill blow holes, honeycombs and surface roughness

PROPERTIES

- Minimal shrinkage/expansion under dry resp. wet curing conditions
- Hydrophobic
- Approval - Standards AS4020:2005 Potable Water
- Open to foot traffic after 3 - 4 hours
- Ready for water pressure after 24 h
- Very good adhesion to concrete and masonry
- 45 min. working time and 12 MPa compressive strength after 4 hours
- Final strength of more than 50 MPa (7250 psi) after 28 days
- Good weathering resistance
- Resists 130 m water pressure acc. to EN 12390-8

TECHNICAL DETAILS

Color	gray
Mixing ratio by weight	100 : 18
Mixing ratio by volume	100 : 28
Density	1.6 kg/l
Substrate temperature	5 - 35 °C (40 - 95 °F)
Water impermeability acc. EN 12390-8	Positive side: 13 bar (190 psi) Negative side: 5 bar (72 psi)
Chloride ions	≤ 0.05 %
Compressive / flexural strength	4 hours: 12 / 2 MPa (1740/290 psi) 24 hours: 24 / 5 MPa (3480/725 psi) 7 days: 38 / 6 MPa (5510/870 psi) 28 days: 53 / 7 MPa (7685/1015 psi)
Adhesive strength	1.6 MPa (232 psi)
Restrained shrinkage	1.5 MPa (218 psi)

APPLICATION GUIDELINES

Surface preparation

VELOSIT WP 101 is designed for mineralic substrates like concrete, masonry or absorptive natural stones.

Substrate must be prepared with sand blasting, shot blasting or ideally high pressure water blasting (> 100 bar/1450 psi) to remove all bond breaking substances. Substrate must be open porous and load bearing. The minimum requirement for adhesive strength is 1.5 MPa (218 psi) and for the compressive strength 25 MPa (3625 psi). Lower strength values can be accepted if lower adhesive strength is acceptable. Active water leaks must be treated and fully stopped with VELOSIT PC 222. Leaking cracks need to be sealed with Hychem Spetec. Blowholes, honeycombs or other surface defects can be filled with VELOSIT WP 101 or the repair mortar VELOSIT RM 202. Before the application of VELOSIT WP 101, dampen the substrate with clean water to a saturated surface dry (SSD) condition.

Processing

Mixing

Mix VELOSIT WP 101 with 17 - 20 % potable water, i.e. 3.4 - 4.0 l water per 20 kg bag. Fill 17 % mixing water (3.4 l per bag) into a suitable bucket and mix the powder with a slow speed drill (300 - 600 rpm) into the water until a lump-free mix is achieved. Add up to 3 % water under stirring to adjust the desired consistency.

The product is workable for 45 - 60 min. at 23 °C.

Brush application

Apply the first coat with a masons brush in crossing applications to the pre-dampened substrate at the specified rate. Second coat can be applied after the first one has gained sufficient strength which is after 3 hours at 23 °C. Colder temperatures extend, warmer temperatures shorten the recoat time.

Trowel application

If building code or specification does not require two coats, VELOSIT WP 101 can be applied in one coat by trowel. Make sure to adjust the consistency to a thixotropic workability. Apply a scratch coat of VELOSIT WP 101 to the damp substrate to fill surface irregularities. Immediately apply the desired material amount with a notched trowel to the substrate. 2 mm dry film thickness can be achieved with a 6 mm notch size and application at a 45° angle. Finish the surface immediately afterwards. Make sure all grooves are completely closed without air entrapment.

Spray application

Use suitable spray machines such as:

- Inotec GmbH: INOMAT-M8
- HighTech GmbH: HighPump Small
- Desoi GmbH: Desoi SP-Y

Fill the product as described under "Mixing" into the feed hopper of the spray machine and spray continuously. VELOSIT WP 101 can be applied in one lift if specification allows. Otherwise spray in two layers with a wait time of approx. 60 min. between coats. Long spray interruptions may result in clogging of the spray hose. The product may cure a lot faster if the hose is exposed to direct sunlight. Always empty and flush the machine after spraying or before long spray interruptions. VELOSIT WP 101 is a fast curing material and may be difficult to remove if left in the machine.

Using as a repair mortar

VELOSIT WP 101 can be used as a repair mortar for small repairs and especially as a cove mortar.

Apply a slurry coat of VELOSIT WP 101 to at on the slab and approx. 25 cm on the lower section of the wall. The cove mortar can be produced with less water addition and can be applied wet in wet onto the slurry coat.

Curing

VELOSIT WP 101 does not require long term curing as it reacts relatively fast with water. Only under hot weather or very dry conditions water curing for 3 - 4 hours is required.

ESTIMATING

Brush application 2 mm:

1 st coat VELOSIT WP 101:	1.6 kg/m ²
2 nd coat VELOSIT WP 101:	1.6 kg/m ²

Trowel application 2 mm

Scratch coat VELOSIT WP 101:	0 - 0.5 kg/m ²
2 nd coat VELOSIT WP 101:	2.7 - 3.2 kg/m ²

Spray application 2 mm:

VELOSIT WP 101:	3.2 kg/m ²
-----------------	-----------------------

Other thickness requirements:

1.6 kg* VELOSIT WP 101 per m² for 1 mm dry film thickness on smooth substrates. Depending on surface roughness application rates can be significantly higher.

* 1.6 kg VELOSIT WP 101 powder + 0.3 kg water, i.e. 1.9 kg mixed material per mm and m²

CLEAN UP

VELOSIT WP 101 can be removed in the fresh state with water. Once it has cured acidic cleaners like muriatic acid are required.

PACKAGING

20 kg watertight plastic bags

STORAGE

In unopened original packs for 12 months at 5 - 35 °C (40 - 95 °F) in a dry storage place protected against sunlight.

SAFETY

Please observe the actual valid material safety data sheet and follow the described safety measures for handling of the product.

NOTE: Customer responsibility

The technical information and application advice given here is based on the best information available at the time of print. As the information herein is of a general nature, no assumption can be made as to the products suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation.

Field support, where provided, does not constitute supervisory responsibility. Suggestions made by HYCHEM either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they and not HYCHEM are responsible for carrying out procedures appropriate to a specific application.

If unsure contact Hychem for further technical advice before proceeding.

≡velosit



HYCHEM

Head Office

Unit 1, 30 Bluett Drive, Smeaton Grange NSW 2567

T 02 4646 1660 F 02 4647 3700 E admin@hychem.com.au W www.hychem.com.au

ISSUE NUMBER 220620